

Fisa tehnica Banda de izolatie din polietilena

| Caracteristici | * | Metoda de incercare | * | Valoare |
|---|---|---|---|---|
| Densitate | * | interna | * | 23/25 kg/m ³ – 30/33 kg/m ³ /100kg |
| Coeficientul de conductie | * | UNI EN12667 | * | Egal cu producerea polietilenei |
| Solicitarea si deformarea La compresia 10% | * | UNI EN 186 | * | 13,002 KPa(testat pe material de 5mm grosime la institut abilitat |
| Temperatura ceruta | * | metoda interna | * | -10° +70°C |
| Rezizenta la ozon | * | | * | Optima |
| Rezistenta la mucegai si Insecte | * | | * | Optima |
| Toxicitate | | ANFOR NF 16-101-1988 ANFOR NF X70/100/2001 ANFOR NF 10-702-1-1995 ANFOR NF 10-702-2-1994 | | raportul de toxicitate inerenta la fum CSI DC 01/494F05 din 07/07/2005 |
| Rezistenta la deformare | * | | * | Optima |
| Nu contine CFC(Freon) | * | | * | Conform |

