



CYCLON HELLAS S.A.
INDUSTRIAL, LUBRICANTS AND PETROLEUM PRODUCTS, PROCESSING
CORPORATION

QUALITY CERTIFICATION

TURBINE ISO 32

TESTS	TY PICAL	METHODS
Specific Graviry at 15°C	0,8750	ASTM D-1298
Visc Kinematic at 100°C,cst	5,28	ASTM D-445
Visc Kinematic at 40°C, cst	31,50	ASTM D-445
Viscosity Index	98	ASTM D-2270
Pour point, °C	-27	ASTM D-97
Colour	L 1,0	ASTM D-1500
Total Acid Number , mg KOH/gr	0,11	ASTM D-974
Flash Point (open tester), °C	232	ASTM D-92
Foam test: tendency, ml max	0-0-0	ASTM D-892 S
Stability, ml max	0-0-0	ASTM D-892 T
Emulsion characteristics,min	10 (40-40-0)	ASTM D-1401
Corrosion copper strip	1a	ASTM D-130
Humidity, WBD %	0	ASTM D 95