



Caracteristici tehnice	Standarde	iQ GRANIT
Tipul acoperitorii de pardoseala	-	Covor PVC Omogen (1 strat)
Clasificare	EN 685	COMERCIAL 34
		INDUSTRIAL 43
	UPEC	U4 P3 E2/3 C2
Grosimea totala	EN 428	2 mm
Grosimea stratului de uzura	EN 429	2 mm
Greutatea totala	EN 430	3.000 g/mp
Ranforsat cu poliuretan (PUR)	-	DA
Grupa de abraziune (pierdere grosime - Partea 1 / pierdere volum Partea 2)	EN 600 Partea 1	Grupa P: $\leq 0,15$ mm
	EN 600 Partea 2	Grupa P: $\leq 4,00$ mm ³
Deformare reziduala	EN 433	cca. 0,03 mm
Testul scaunului cu rotile	EN 425	INDEPLINIT
Stabilitate dimensionala	EN 434	$\leq 0,4$ %
Deformare la caldura	EN 434	≤ 8 mm
Reactia la foc	DIN 4102	B1
	EN ISO 9239-1	≥ 8 kW/mp
	EN ISO 13501-1	B _{fl} s1
	EN ISO 11925-2	Indeplinit
	BS 476: Part 7, 1977	Clasa 2
Rezistenta la alunecare	DIN 51130	R9
	EN 13893	$\geq 0,30$ mm
Proprietati electrostatice	EN 1815	< 2 kV
Absorbtia fonica la impact	EN ISO 717/2	$\Delta L_w =$ cca. +4 dB
Rezistenta la razele ultraviolete	EN ISO 105-B02	≥ 6
Rezistenta chimica	EN 423	Rezistenta buna
Rezistenta la bacterii si ciuperci	NF EN ISO 846-A/C	NU FAVORIZEAZA CRESTEREA
Rezistenta termica	EN 12524	0,0095 mp K/W
Incalzire in pardoseala	DIN 52612	Pretabil - max. 27 °C
Culori	-	24
Dimensiuni de livrare	EN 426	Rola: 25 m x 2 m (50 mp/rola)
	EN 427	Dale: 61 cm x 61 cm

